


# OptiLite 75 Xtra

## OPTICAL & SOLAR PROPERTIES

|                                  | Single Pane | Double Pane |
|----------------------------------|-------------|-------------|
| Visible Light Transmitted        | 76 %        | 69 %        |
| Visible Light Reflected (Int)    | 9 %         | 17 %        |
| Visible Light Reflected (Ext)    | 9 %         | 15 %        |
| Ultra Violet Block               | 99 %        | 99 %        |
| Total Solar Energy Reflected     | 8 %         | 10 %        |
| Total Solar Energy Transmitted   | 39 %        | 34 %        |
| Total Solar Energy Absorbed      | 53 %        | 56 %        |
| Emissivity (Room Side)           | 0.84        | 0.84        |
| Glare Reduction                  | 16 %        | 15 %        |
| Shading Coefficient              | 0.62        | 0.50        |
| Solar Heat Gain Coeff. (G-Value) | 0.54        | 0.43        |
| U-Value Winter (IP)              | 1.04        | 0.48        |
| U-Value Winter (SI)              | 5.91        | 2.73        |
| Luminous Efficacy                | 1.20        | 1.38        |
| Total Solar Energy Rejected      | 46 %        | 57 %        |

R09275X - OptiLite 75 Xtra Pressure Sensitive Adhesive



ED-A DS No 1446 August 2011